

BERLIN – Semi Aniline

Technical specifications

Average size: ca. 4,50 m²

Thickness: ca. 1,4 mm

Raw material: Australian raw hides

Tanning: Chrome

	Metode	Testresultat
Light fastness	IUF 402 / UNI EN ISO 105-B02	5 blue scale
Rubbing fastness, dry, 500 rubbings	IUF 450 / UNI EN ISO 11640	≥ 4 grey scale
Rubbing fastness, wet, 80 rubbings	IUF 450 / UNI EN ISO 11640	≥ 4 grey scale
Rubbing fastness, sweat, 40 rubbings	IUF 450 / UNI EN ISO 11640	≥ 4 grey scale
Tearing strength	IUP 40 / UNI EN ISO 3377-1	≥20 N/mm
Flexing endurance	IUP 20 / UNI EN ISO 5402	≥30.000
Adhesion og finish	IUF 470 / UNI EN ISO 11644	≥3,5 N/cm

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flammability test:

The material fulfils the requirements according to:

UNI EN ISO 1021-1/2

BS 5852 1991 Sec. 4 NI/0-1

California T.B. 117