

RIO – Semi Aniline

Technical specifications

Average size: 5 m²
Thickness: 1,0-1,2 mm

Raw material: European rawhides
Tanning: Chrome

	Metode	Testresultat
Light fastness	UNI EN ISO 105-B02	≥3
Rubbing fastness, dry, 200 rubbings	UNI EN ISO 11640	≥ 3
Rubbing fastness, wet, 80 rubbings	UNI EN ISO 11640	≥ 3
Rubbing fastness, sweat, 80 rubbings	DIN EN ISO 11640	≥ 3
Tearing strength	DIN EN ISO 3377-1	≥20 N
Flexing endurance	DIN EN ISO 5402	≥20.000

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flammability test:

The material fulfils the requirements according to:

UNI EN ISO 1021-1/2

BS 5852/1