

MADRID – Corrected leather

Technical specifications

Average size: 5,2 m²
Thickness: 1,2-1,4 mm

Raw material: Brazilian raw hides
Tanning: Chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02	Min. 4
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640/11641	4
Rubbing fastness, wet, 250 rubbings	DIN EN ISO 11640/11641	4
Rubbing fastness, sweat, 80 rubbings	DIN EN ISO 11640/11641	4
Flexing endurance	DIN EN ISO 5402-1	20.000
Tearing strength	DIN EN ISO 3377-2	Min. 40 N/mm
Finish Adhesion	DIN EN ISO 11644	Min. 3 N/cm
PH value	DIN EN ISO 4045	Min. 3,2

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 1990 Sec. 4 NI/0-1,

California T.B. 117-2013 section 1