

## MIAMI – Slightly Corrected Semi Aniline leather

### Technical specifications

Average size: 4,5 m<sup>2</sup>  
Thickness: 1,1-1,3 mm

Raw material: European raw hides  
Tanning: Chrome free

	Method	Test result
Light fastness		≥6
Rubbing fastness, dry, 500 rubbings	IUF 450/UNI EN ISO 11640	≥= 4 grey scale
Rubbing fastness, wet, 150 rubbings	IUF 450/UNI EN ISO 11640	≥= 4 grey scale
Rubbing fastness, sweat, 80 rubbings	IUF 450/UNI EN ISO 11640	≥= 4 grey scale
Flexing endurance	IUP 40 / UNI EN ISO 5402	>=30.000
Tearing strength	IUP	>=20 N/mm
PH value		≥3,5
Finish adhesion (dry)		≥2,5 N/cm

Chrome free tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

#### **Flammability test:**

The material fulfils the requirements according to:

UNI EN ISO 1021-1/2

BS 5852 2006 Sec. 4 NI/0-1

California T.B. 117