

MONTANA – Aniline leather

Technical specifications

Average size: 5,0 m²
Thickness: 1,4-1,6 mm

Raw material: European rawhides
Tanning: Chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02 / IUP20	≥3
Rubbing fastness, dry, 50 rubbings	DIN EN ISO 11640 / IUF 450	≥3 (black ≥2)
Rubbing fastness, wet, 20 rubbings	DIN EN ISO 11640/ IUF 450	≥3 (black ≥2)
Rubbing fastness, sweat, 20 rubbings	DIN EN ISO 11640/ IUF 450	≥3 (black ≥2)
Flexing endurance	DIN EN ISO 5402 /IUP 20	≥30.000

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfils the requirements according to:
UNI EN ISO 1021-1/2,
BS 5852 1990 Sec. 4 NI/0-1,
California T.B. 117-2013 section 1