

PALOMA – Light Corrected Semi Aniline

Technical specifications

Average size: 4,8 m²
Thickness: 1,0-1,2 mm

Raw material: European raw hides
Tanning: Chrome Free

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥6
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, wet, 80 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, sweat, 50 rubbings	DIN EN ISO 11640	≥4
Tear strength	DIN EN ISO 3377-1	≥20 N/mm
Flex endurance	DIN EN ISO 5402	30.000
PH value	DIN ISO 4045	≥3,5
Finish Adhesion	DIN EN ISO 11644 / 5402	≥2,5 N/cm

Chrome free tanned and without the use of PCP and CFC which are damaging to the environment.
PALOMA leather is Chrome free (FOC) and complies standard for the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:

UNI EN ISO 1021-1/2

BS5852 Crib 5

ÖNORM B3800

ÖNORM B3825

DIN 5510-2 "Papierkissen-Test"

IMO-Res. A 652 (16)

California T.B. 117-2013 section 1