

## SCANDINAVIAN – Semi Aniline leather

### Technical specifications

Average size: 5,5 m<sup>2</sup>  
Thickness: 1,1-1,3 mm

Raw material: South German raw hides  
Tanning: Chrome

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥4
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, wet, 250 rubbings	DIN EN ISO 11640	≥3/4
Rubbing fastness, sweat, 80 rubbings	DIN EN ISO 11640	≥3/4
Flex endurance	DIN EN ISO 5402	50.000
Finish Adhesion	DIN EN ISO 11644 / 5402	≥2 N/cm
Tear strength	DIN EN ISO 3377-1	≥20 N/mm

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

#### **Flame resistance:**

The material fulfils the requirements according to:

UNI EN ISO 1021 – 1/2

BS 5852 1991 Crib 5

California T.B. 117-2013 section 1