

SYDNEY – Semi Aniline Leather

Technical specifications

Average size: 4,2 m²
Thickness: 0,9-1,1 mm

Raw material: Australia, New Zealand, or European raw hides
Tanning: Chrome

	Method	Test result
Light fastness	IUF 402 / DIN EN ISO 105-B02	5
Rubbing fastness, dry, 500 rubbings	IUF 450 / DIN EN ISO 11640	≥4
Rubbing fastness, wet, 150 rubbings	IUF 450 / DIN EN ISO 11640	≥4
Rubbing fastness, perspiration, 80 rubbings	IUF 450 / DIN EN ISO 11640	≥4
Adhesion of finish	IUF 470 / DIN EN ISO 11644	3,5 N/Cm
Tear strength	IUP 40 / UNI EN ISO 3377-1	≥20 N
Flexing endurance	IUP 20 / DIN EN ISO 5402	30.000

Chrome tanned and produced without the use of PCP and CFC which are damaging to the environment. The leather complies with all limits and standards for chrome VI and the REACH declaration.

Flame resistance:

The material fulfills the requirement according to:
UNI EN ISO 1021-1/2
BS5852 1991 Sec. 4 NI/0-1,
California T.B.117