

ONE – Technical Data

ONE is a lightly buffed vintage leather with a raw and distinctive character. The refined surface and the high quality of the leather create a comfortable and natural seating experience, making the material ideal for furniture where both aesthetics and functionality are essential.

The leather has a vibrant and natural appearance with beautiful colour variations and a pronounced structure that highlights the authenticity of the material. The surface provides a warm and tactile feel, adding personality and character to any piece of furniture.

ONE is a highly versatile leather that is perfectly suited for both private homes and for interiors in hotels, restaurants, and other environments where the natural and rustic look of leather is appreciated.

To preserve its authenticity, ONE is available in only one colour – HENNESY – a small tribute to the characteristic whisky tone that the leather resembles.

Note

Aniline leather is an untreated, highly natural leather where colour variations may occur and all natural markings are visible and form part of its character.

It is extremely soft and breathable with high comfort, but has no protective surface.

Extra care is recommended for this type of leather, as it is highly sensitive to stains, sunlight, and wear.

For more detailed information, please visit our website: <https://ca-mo.com/en/laedertype/anilin-laeder/>

Product Information

- **Leather type:** Lightly buffed vintage aniline leather
- **Application:** Furniture – residential and contract (hotels and restaurants)
- **Average hide size:** approx. 4.5 m²
- **Thickness:** 0.9 – 1.1 mm
- **Raw material:** New Zealand hides
- **Tanning:** Chrome tanned
- **Environment:** Produced without the use of PCP and CFC and complies with all limits and standards for Chromium VI as well as the REACH declaration

Fire Test – The article meets the requirements according to:

UNI EN ISO 1021 – 1/2

BS 5852 UK Match & Cigarette Test

California T.B. 117

	Method	Test result
Light resistance	IUF 402 / UNI EN ISO 105-B02	3 blue scale
Rubbing resistance, dry, 50 rubbings	IUF 450 / UNI EN ISO 11640	≥ 4 grey scale
Tear strength	IUP 40 / UNI EN ISO 3377-1	≥ 20 N
Flexing endurance	IUP 20 / UNI EN ISO 5402	≥ 30.000