

PALOMA – Technical Data

PALOMA is an elegant and timeless semi-aniline leather that offers a beautiful, uniform appearance with a warm and soft touch. The leather combines aesthetics, comfort, and functionality, adding a calm and exclusive character to furniture that endures over time.

The supple surface and pleasant feel make PALOMA ideal for all types of upholstery where both seating comfort and visual quality are essential. The leather is developed to withstand daily use and is therefore well suited for both private homes and demanding contract environments where durability and easy maintenance are key factors.

PALOMA is also an excellent choice for projects with a focus on responsible materials. The leather is chrome-free (FOC) and certified with IMO, documenting a product that meets high standards in terms of environment, health, and safety.

Note

Semi aniline leather has a protective surface while still maintaining a natural appearance. Minor variations in colour and texture may occur and are part of the leather's character.

Regular care is recommended to maintain the leather's softness and appearance.

For more detailed information, please visit: <https://ca-mo.com/en/laedertype/semi-anilin-laeder/>

Product Information

- **Leather type:** Semi aniline leather
- **Application:** All types of upholstery – residential and contract (including marine interiors)
- **Certifications:** IMO
- **Average hide size:** approx. 4.8 m²
- **Thickness:** 0.9 – 1.3 mm
- **Raw material:** European hides
- **Tanning:** Chrome-free (FOC)
- **Environment:** Produced without the use of PCP and CFC and complies with all limits and standards in accordance with the REACH declaration

Fire Test – The article meets the requirements according to:

UNI EN ISO 1021 – 1/2

BS 5852 UK Match & Cigarette Test

BS 5852 Crib 5

California T.B. 117

IMO Resolution A.652 (16)

ÖNORM B3825 – Hardly inflammable

ÖNORM B3800 – Smoke density / dripping

DIN 5510-2 – “Papierkissen-Test”

	Method	Test result
Light fastness	DIN EN ISO 105-B02	≥6
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, wet, 80 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, sweat, 50 rubbings	DIN EN ISO 11640	≥4
Tearing strength	DIN EN ISO 3377-1	≥20 N/mm
Flexing endurance	DIN EN ISO 5402	30.000
Finish Adhesion	DIN EN ISO 11644 / 5402	≥2,5 N/cm
PH value	DIN ISO 4045	≥3,5