

SILK – Technical Data

SILK is a modern and smooth aniline leather with a unique silky surface that adds a sophisticated and exclusive expression to any design project.

For architects and designers working with materiality and detailing, SILK offers a distinctive combination of aesthetics and tactility. The silky-soft surface, natural breathability, and beautiful patina development over time make the leather ideal for projects where both comfort and visual elegance are essential.

The colour palette is developed with a focus on modern and international environments, supporting contemporary architectural trends – from minimalist interiors to warm spaces with depth and character. As an aniline leather, SILK develops a beautiful and personal patina over time, making it particularly attractive in projects where the ageing of materials becomes an integral part of the design narrative.

Note

Aniline leather is an untreated, highly natural leather where colour variations may occur and all natural markings are visible and form part of its character.

It is extremely soft and breathable with high comfort, but has no protective surface.

Extra care is recommended for this type of leather, as it is highly sensitive to stains, sunlight, and wear.

For more detailed information, please visit our website: <https://ca-mo.com/en/laedertype/anilin-laeder/>

Product Information

- **Leather type:** Aniline leather
- **Application:** Upholstery and modern design projects – residential and contract
- **Average hide size:** approx. 4.5 m²
- **Thickness:** 1.0 – 1.2 mm
- **Raw material:** European hides
- **Tanning:** Chrome tanned
- **Environment:** Produced without the use of PCP and CFC and complies with all limits and standards for Chromium VI as well as the REACH declaration

Fire Test – The article meets the requirements according to:

UNI EN ISO 1021 – 1/2

BS 5852 UK Match & Cigarette Test

California T.B. 117

	Method	Test result
Light fastness	DIN EN ISO 105-B02 / IUF 402	3
Rubbing fastness, dry, 100 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, wet, 20 rubbings	DIN EN ISO 11640	≥4
Rubbing fastness, sweat, 20 rubbings	DIN EN ISO 11640	≥4
Flexing endurance	DIN EN ISO 5402-1 / IUP 20	≥30.000
Tearing strength	DIN EN ISO 3377-1 / IUP 40	≥20 N/cm
Adhesion of finish	DIN EN ISO 11644 / IUF 470	≥3,50 N/cm