VICTORIA – Technical Data

VICTORIA is a beautiful and exclusive wild aniline leather, produced from the finest European raw materials. Wild aniline leather highlights the life of the animal to an even greater extent, with more visible traces of scars, marks, and other natural variations in the hide. The velvety-soft and breathable surface gives the leather a refined, natural appearance and a unique level of comfort that only genuine aniline leather can offer.
As an exclusive natural product, VICTORIA develops a beautiful patina over time, adding even more character and depth to its expression. The high seating comfort makes it particularly suitable for upholstery of sofas and chairs, as well as for furnishing exclusive environments such as bars, hotels, and other design projects where quality and aesthetics are in focus.

Note
Aniline leather is an untreated, highly natural leather where colour variations may occur and all natural markings are visible and form part of its character.
It is extremely soft and breathable with high comfort, but has no protective surface.
Extra care is recommended for this type of leather, as it is highly sensitive to stains, sunlight, and wear.
For more detailed information, please visit our website: https://ca-mo.com/en/laedertype/anilin-laeder/

Product Information

- **Leather type:** Wild aniline leather
- **Application**: Upholstery of sofas and chairs as well as exclusive bars, hotels, and interior projects
- **Average size per hide:** approx. 5.5 m²
- **Thickness:** 1.3 – 1.5 mm
- **Raw materials:** European hides
- **Tanning:** Chrome tanned
- **Environment:** Produced without the use of PCP and CFC and complies with all limits and standards for Chromium VI as well as the REACH declaration

---

Fire Test – The article meets the requirements according to:
UNI EN ISO 1021 – 1/2
BS 5852 UK Match & Cigarette Test
California T.B. 117

	Method	Test result
Light fastness	UNI EN ISO 105-B02	>3
Rubbing fastness, dry, 50 rubbings	UNI EN ISO 11640	>3
Rubbing fastness, wet, 20 rubbings	UNI EN ISO 11640	>3
Rubbing fastness, sweat, 10 rubbings	UNI EN ISO 11640	>3
Tearing strength	UNI EN ISO 3377-1	> 20 N/mm