

## MALAGA – Technical Data

MALAGA is an exclusive semi-aniline leather with natural grain, exceptional softness, and a beautiful, natural appearance that gives furniture a sophisticated and luxurious look. The leather combines high seating comfort with durability and feels wonderful to the touch.

MALAGA is available in a carefully curated palette of contemporary and elegant colours, perfectly suited for modern homes and contract projects. It is ideal for soft upholstery such as sofas, armchairs, and cushions, where both design and comfort are paramount.

With MALAGA, you can create furniture that is both visually appealing and incredibly comfortable - a leather choice that elevates any furniture.

### Note

Semi aniline leather has a protective surface while still maintaining a natural look. Minor variations in colour and texture may occur and are part of the leather's character.

Regular care is recommended to maintain the leather's softness and appearance.

For more detailed information, please visit: <https://ca-mo.com/en/laedertype/semi-anilin-laeder/>

---

### Product Information

- **Leather type:** Semi aniline leather
- **Applications:** Soft upholstery such as sofas, chairs, and cushions – residential and contract
- **Average hide size:** approx. 4.5 m<sup>2</sup>
- **Thickness:** 1.2 – 1.4 mm
- **Raw material:** Australian hides
- **Tanning:** Chrome tanned
- **Environment:** Produced without PCP and CFC and complies with all limits and standards for Chromium VI as well as the REACH declaration

---

**Fire Test** – The article meets the requirements according to:

IMO MSC.307 (88) – Annex 1 – Part 8

UNI EN ISO 1021 – 1/2

California T.B. 117

	Method	Test result
Light fastness	DIN EN ISO 105-B02	5
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640	≥ 4
Rubbing fastness, wet, 150 rubbings	DIN EN ISO 11640	≥ 4
Rubbing fastness, sweat, 80 rubbings	DIN EN ISO 11640	≥ 4
Finish Adhesion	DIN EN ISO 11644	≥ 2 N/cm
Flexing endurance	DIN EN ISO 5402	≥ 30.000
Tearing strength	DIN EN ISO 3377-1	≥ 20 N