

## SYDNEY FOC – Technical Data

SYDNEY FOC is the chrome-free version of our popular SYDNEY – a characterful semi-aniline leather that combines warmth, comfort, and a modern expression with a more responsible material choice. The leather retains the same inviting and relaxed look, but is developed without the use of chrome, making it an ideal choice for projects with a focus on sustainability.

The soft and supple structure ensures a high level of seating comfort while highlighting the natural character of the leather. At the same time, the durable finish provides good wear resistance, making it suitable for everyday use. SYDNEY FOC therefore performs equally well in private homes and in demanding contract environments where both functionality and aesthetics are essential.

With its versatile expression and comfortable surface, SYDNEY FOC is an excellent choice for furniture where an exclusive look is desired without compromising on durability – now in a chrome-free version.

### Note

Semi aniline leather has a protective surface while still maintaining a natural appearance. Minor variations in colour and texture may occur and are part of the leather’s character.

Regular care is recommended to maintain the leather’s softness and appearance.

For more detailed information, please visit: <https://ca-mo.com/en/laedertype/semi-anilin-laeder/>

---

### Product Information

- **Leather type:** Semi aniline leather
- **Application:** Furniture – residential and contract
- **Average hide size:** approx. 4.2 m<sup>2</sup>
- **Thickness:** 0.9 – 1.1 mm
- **Raw material:** European hides
- **Tanning:** Chrome-free (FOC)
- **Environment:** Produced without the use of PCP and CFC and complies with all limits and standards in accordance with the REACH declaration

---

**Fire Test** – The article meets the requirements according to:

UNI EN ISO 1021 – 1/2

BS 5852 UK Cigarette & Match Test

California T.B 117

	Method	Test result
Light fastness	IUF 402 / DIN EN ISO 105-B02	5
Rubbing fastness, dry, 500 rubbings	IUF 450 / DIN EN ISO 11640	≥4
Rubbing fastness, wet, 150 rubbings	IUF 450 / DIN EN ISO 11640	≥4
Rubbing fastness, perspiration, 80 rubbings	IUF 450 / DIN EN ISO 11640	≥4
Adhesion of finish	IUF 470 / DIN EN ISO 11644	3,5 N/Cm
Tear strength	IUP 40 / UNI EN ISO 3377-1	≥20 N
Flexing endurance	IUP 20 / DIN EN ISO 5402	30.000