

SIERRA WHEELMARK – Technical Data

SIERRA WHEELMARK “Nautica Marine” is a corrected leather with a fine, classic embossing that creates a beautiful and uniform texture. With its IMO certification, SIERRA WHEELMARK is the ideal choice for interiors on cruise ships, yachts, and within the marine industry, where exceptionally high standards for fire safety, durability, and certification are required. The leather is also highly suitable for other demanding contract environments where materials are exposed to intensive use over extended periods.

The protective surface makes SIERRA WHEELMARK easy to work with and simple to maintain. The article is suitable for upholstering both soft and hard surfaces such as chairs, sofas, benches, wall panels, and custom interior solutions, where a durable leather with a consistent and elegant appearance is desired. SIERRA WHEELMARK is available in a wide range of contemporary colours, offering great design flexibility and making it possible to create both subtle and bold interior solutions.

Note

Corrected leather has a protective surface that ensures high durability, easy maintenance, and a uniform appearance.

Regular care is recommended to maintain the leather’s softness and appearance.

For more detailed information, please visit: <https://ca-mo.com/en/laedertype/korrigeret-laeder/>

Product Information

- **Leather type:** Corrected leather
- **Application:** All types of upholstery – particularly suitable for marine and contract markets
- **Certification:** IMO
- **Average hide size:** approx. 4.4 m²
- **Thickness:** 0,8 – 1.0 mm
- **Raw material:** Produced in Italy from Brazilian hides
- **Tanning:** Chrome tanned
- **Environment:** Produced without the use of PCP and CFC and complies with all limits and standards for chromium VI as well as the REACH declaration

Fire Test – The article meets the requirements according to:

IMO MSC.307 (88) – Annex 1 – Part 8

UNI EN ISO 1021 – 1/2

California T.B. 117

	Method	Test result
Light fastness	DIN EN ISO 105-B02	5
Rubbing fastness, dry, 500 rubbings	DIN EN ISO 11640	≥ 4
Rubbing fastness, wet, 150 rubbings	DIN EN ISO 11640	≥ 4
Rubbing fastness, sweat, 80 rubbings	DIN EN ISO 11640	≥ 4
Finish Adhesion	DIN EN ISO 11644	≥ 2 N/cm
Flexing endurance	DIN EN ISO 5402	≥ 30.000
Tearing strength	DIN EN ISO 3377-1	≥ 20 N